

# **DUNBAR – 1625W**

2:1 SHRINK RATIO, DUAL-WALL, FLEXIBLE, POLYOLEFIN TUBING

### **Applications**

DUNBAR-1625W is designed for general purpose applications such as the insulation and strain relief of electrical connections and terminations, light-duty harnessing, jacketing and bundling. The adhesive lining forms an environmental seal that helps protect against moisture.

#### **Features**

- ★ Shrink ratio: 50% or more in the radial direction, 5% or less in the axial direction
- ★ In stock for immediate shipments
- ★ Continuous operating temperature: 55 °C (-67 °F) to 110 °C (230 °F)
- ★ Flammability: UL VW-1 (Jacket only except clear)
- ★ Excellent electrical properties

#### **Standard**

- ★ AMS-DTL-23053/4 Class 2 (Formerly MIL-DTL-23053/4 Class 2)
- ★ UL 224 (File Number: E319314)
- ★ RoHS Compliant

# **Specification Values**

Property			Test Method	Value		
Physical	Unaged	Tensile strength	ASTM D638	Min. 1500 psi		
		Elongation	ASTIVI DOSO	Min. 200%		
	Fluid	Tensile strength	ASTM D638	Min. 1000 psi		
	Resist.	Dielectric strength	ASTM D2671	Min. 400 Volts/mil		
	Heat sho	ck	250 ℃/4 hrs	No cracks, flowing, or dripping		
	Low temperature flex		ASTM D746	No crack @-55°C		
	Secant Modulus		ASTM D882	Max. 25,000 psi		
	Heat Resistance		ASTM D2671	No cracks		
Electrical	Dielectric	strength	ASTM D2671	Min. 500 Volts/mil		
	Volume resistivity		ASTM D876	Min. $1x10^{12}\Omega$ - cm		
Chemical	Copper corrosion		121°C/16hrs	No corrosion		
	Fungus resistance		ASTM G21	No growth		
	Water Ab	sorption	ASTM D570	Max. 0.5%		
	Flammab	oility	ASTM D2671	Pass		


Rev. Feb 2015





# **DUNBAR - 1625W**

2:1 SHRINK RATIO, DUAL-WALL, FLEXIBLE, POLYOLEFIN TUBING



Fully recovered after heating

## **Product Dimensions**

### Minimum Shrink Temperature: 120 ℃

	Expanded Internal Diameter Minimum (D)		Recovered						
Size			Internal Diameter Maximum (d)		Minimum Total Wall Thickness (Total Wall) (T)		Nominal Wall Thickness (Adhesive Wall) (t)		
Inch Size	ln.	mm	ln.	mm	ln.	mm	ln.	mm	
1/8"	0.138	3.51	0.062	1.57	0.017	0.43	0.004	0.102	
3/16"	0.197	5.01	0.093	2.36	0.017	0.43	0.004	0.102	
1/4"	0.238	6.06	0.125	3.18	0.024	0.61	0.004	0.102	
3/8"	0.355	9.02	0.187	4.75	0.024	0.61	0.004	0.102	
1/2"	0.475	12.07	0.250	6.35	0.025	0.64	0.005	0.127	
3/4"	0.712	18.08	0.375	9.53	0.030	0.76	0.005	0.127	
1"	0.950	24.13	0.500	12.70	0.035	0.89	0.007	0.178	
1-1/2"	1.425	36.20	0.750	19.05	0.039	0.99	0.007	0.178	

Rev. Feb 2015

