



- Extreme Abrasion And Cut Resistance
- Resists Gasoline, UV, Solvents, Salt Water And Chemicals
- Braided From .15 mil PET Monofilament

Nominal Size	Part #	Expansion Range		Bulk Spool	Shop Spool	Available Colors	Lbs/100'
		Min	Max				
1/8"	HWN0.13BK	1/16"	3/16"	500'	125'	BK	0.27
3/8"	HWN0.38	3/16"	3/4"	500'	100'	3	0.82
5/8"	HWN0.63	5/16"	7/8"	250'	75'	3	1.10
1"	HWN1.00	1/2"	1 1/2"	250'	50'	3	1.60
1 1/2"	HWN1.50	3/4"	2"	250'	50'	3	2.50
2"	HWN2.00	1 1/2"	3"	200'	50'	3	3.40
3"	HWN3.00	2"	4"	100'	50'	3	4.20
4"	HWN4.00	2 1/2"	5 1/2"	100'	50'	3	4.20



Cut Cleanly
Hot Knife

Material

Polyethylene Terephthalate

Grade

HWN

Monofilament Diameter

.015"

Drawing Number

TF001HWN-WD

50% Thicker For The Really Abrasive Jobs

When your application calls for more protection than our 10 mil products provide, our 15 mil HW is the ideal solution.

HW is commonly used in industrial and marine applications where extreme abrasion protection is critical. The durability of HW makes it ideal for protecting hoses and cables that have to withstand constant contact with rough and abrasive surfaces.

HW is the perfect solution for use on chains and cables to protect painted or laminated surfaces from scuffing and wear.

HW protects trailer hitch harnesses from abrasion, flying debris and UV damage without affecting flexibility or trapping moisture like convoluted tubing.


Colors Available:



Clear (CL), Carbon (CB), and Black (BK).

Colors Available:

3 = BK, CL, and CB.




TECHFLEX
Braided Sleeving Products

www.techflex.com

800.323.5140 • 973.300.9242 • fax: 973.300.9409
104 Demarest Road • Sparta, NJ 07871





ABRASION FLAMMABILITY

Abrasion Resistance
Medium

Rating _____ UL94VO

Abrasion Test Machine
Taber 5150

Abrasion Test Wheel
Calibrase H-18

Abrasion Test Load
500g

Room Temperature
80°F

Humidity
72%

Two Broken Strands
200 Test Cycles

Braid Worn Through In
One Direction, In Several
Places
700 Test Cycles

Material Destroyed -
Braid Worn Through In
Both Directions
950 Test Cycles

Pre-Test Weight
5,262.7 mg

Post-Test Weight
4,979.9 mg

Test End Loss Of Mass
Point Of Destruction
239.3 mg

CHEMICAL RESISTANCE


1=No Effect 4=More Affected
2=Little Effect 5=Severely Affected
3=Affected

Aromatic Solvents _____	2
Aliphatic Solvents _____	1
Chlorinated Solvents _____	3
Weak Bases _____	1
Salts _____	1
Strong Bases _____	2
Salt Water 0-S-1926 _____	1
Hydraulic Fluid MIL-H-5606 _____	1
Lube Oil MIL-L-7808 _____	1
De-Icing Fluid MIL-A-8243 _____	1
Strong Acids _____	3
Strong Oxidants _____	2
Esters/Ketones _____	1
UV Light _____	1
Petroleum _____	1
Fungus ASTM G-21 _____	1
Halogen Free _____	Yes
RoHS _____	Yes
SVHC _____	None

Melt Point
ASTM D-2117
482°F (250°C)

Maximum Continuous
Mil-I-23053
257°F (125°C)

Minimum Continuous
-94°F (-70°C)



PHYSICAL PROPERTIES

Monofilament Diameter _____	.015"
ASTM D-204	
Flammability Rating _____	UL94
Recommended Cutting _____	Hot Knife
Colors _____	3
Wall Thickness _____	.038"
Tensile Strength (Yarn) _____	10
ASTM D-2256 Lbs	
Specific Gravity ASTM D-792 _____	1.38
Moisture Absorption _____	.1-2
% ASTM D-570	
Hard Vacuum Data _____	
ASTM E-595 at 10-5 torr	
TML _____	.19
CVCM _____	.00
WVR _____	.16
Smoke D-Max _____	56
ASTM E-662	
Outgassing _____	Med
Oxygen Index _____	21
ASTM D-2863	

© 2020 Techflex® - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex® is strictly forbidden.

Techflex® product names and logos are registered trademarks of Techflex®, unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex® makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's® only obligations are those in standard terms of sale for these products and Techflex® will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications.